

## Aradur<sup>®</sup> 140-2 BD Hardener

### Product Description

Aradur<sup>®</sup> 140-2 BD Hardener is a medium viscosity, polyamide hardener. When used to cure Araldite<sup>®</sup> low molecular weight solid epoxy resins, it can provides some coating systems with excellent flexibility, toughness and good overall performance properties. .

### Applications

- General purpose industrial coatings
- Adhesives
- Maintenance coatings
- 
- Mortars and mastics
- Potting compounds

### Features

- Excellent water resistance
- Excellent mechanical properties
- Excellent corrosion resistance
- Excellent adhesion
- Good electrical properties
- Complies with FDA 21 CFR 175.300

### Typical Properties\*

Property	Aradur <sup>®</sup> 140-2 BD
Appearance	Clear, no contamination
Color, Gardner, max	10
Amine value, mg KOH/g	370 - 410
H <sup>+</sup> active equivalent, g/eq	70 - 115
Viscosity@ 40°C, cP	3000 - 6000
@ 75°C, cP	300 - 600
Density @ 25°C (77°F), g/cm <sup>3</sup>	0.96
Flash point, closed cup, °C (°F)	>93 (>200)

\*Typical properties are based on Huntsman's test methods. Copies are available upon request.

## Processing

Aradur<sup>®</sup> 140-2 BD hardener may be used to cure both Araldite<sup>®</sup> liquid and low molecular weight solid epoxy resin solutions at ambient or slightly elevated temperatures. The normal mixing ratio of Aradur<sup>®</sup> 140-2 hardener to epoxy resin is 35 to 60 parts per hundred parts of Araldite<sup>®</sup> GY 6010 epoxy resin. The ratio of epoxy resin to polyamide resin will determine the ultimate coating properties. The cure schedule depends upon the total formulation used (i.e., resin, hardener, pigmentation, solvents) and the conditions of application (i.e., temperature, film thickness, etc.). Longer curing times will be required at lower temperatures.

Reactivity increases throughout the polyamide series of Aradur<sup>®</sup> 115, Aradur<sup>®</sup> 125 BDB, and Aradur<sup>®</sup> 140-2 hardeners. The degree of sensitivity to high atmospheric humidity increases in proportion with the amine content.

## Unpigmented Coating

Product	Pounds	Gallons
Part A		
Araldite <sup>®</sup> GY 507 <sup>1</sup>	682.8	71.90
Part B		
Aradur <sup>®</sup> 140-2 BD	227.6	28.10
Total (Parts A&B)	910.4	100.00

<sup>1</sup>Modified liquid epoxy resin (EEW = 180 –192 g/eq)<sup>2</sup>Nyral 3X, R.T. Vanderbilt Co. or equal

## Unpigmented Coating Physical Constants (mix)

Property	Value
Non-volatile content, %	100.0
Epoxy/hardener weight ratio	100/33
Weight per gallon @ 25°C, lb/gal	9.1
Pot life @ 25°C, h	3.0
Viscosity @ 25°C, KU	98

### Unpigmented Coating Performance

Property	Value
Substrate	Steel
Cure Schedule	7 days @ 25°C, 50% RH
Film thickness, mils	3.5
Dry time, 25°C, hr set-to-touch paper free	>7.0 24.0
Flexibility, 1/8" mandrel	Pass
Adhesion	Good

### Unpigmented Coating Chemical Resistance, 25°C (77°F) (continuous immersion)

Reagent	Value
Water, 7 days	No effect
MIBK	Slight film softening
10% NaOH	No effect
10% HCl	Few No. 9 blisters

### White Gloss Enamel

Product	Pounds	Gallons
Part A		
Araldite® GY 507	543.2	56.00
Titanium Dioxide	517.7	15.16
Part B		
Aradur® 140-2 BD	233.6	28.84
Total (Parts A&B)	1294.5	100.00

<sup>1</sup>Modified liquid epoxy resin (EEW = 180 –192 g/eq)<sup>2</sup>Nyral 3X, R.T. Vanderbilt Co. or equal

### White Gloss Enamel Physical Constants (mix)

Property	Value
Non-volatile content, %	100.0
Epoxy/hardener weight ratio	100/43
Pigment binder ratio	40/60
Weight per gallon @ 25°C, lb/gal	12.9
Pot life @ 25°C, h	1.75
Viscosity @ 25°C, cP	60,000

### White Gloss Enamel Performance

Property	Value
Substrate	Steel
Cure Schedule	7 days @ 25°C, 50% RH
Film thickness, mils	12
Dry time, 25°C, hr set-to-touch	1.0
paper free	6.5
Flexibility, 1/8" mandrel	Fail
Adhesion	Good

### White Gloss Enamel Chemical Resistance, 25°C (77°F) (continuous immersion)

Reagent	Value
Water, 7 days	No effect
MIBK, 3 h	No effect
10% NaOH, 7 days	No effect
10% HCl, 3 h	No effect

Additionally, the use of Aradur<sup>®</sup> 140-2 BD hardener in a flooring formulation gives overall good chemical resistance and very good mechanical properties

### Epoxy Flooring

Product	Parts by weight
Araldite <sup>®</sup> GY 6010	100
Araldite <sup>®</sup> RD-1 (Butyl glycidyl ether)	10
Aradur <sup>®</sup> 140-2 BD	45
Accelerator 960-1	2 - 3
Dimethylaminoethanol	3 - 5
Bettle 216-8 <sup>2</sup>	1 - 3
Cure Schedule	7 days at R.T.

<sup>2</sup>American Cyanamid or equal

### Epoxy flooring Mechanical Properties

Property	Value
Shrinkage during cure, in/in	0.0008 - 0.0015
Coefficient of thermal expansion, x 10 <sup>-6</sup> linear/°C	50
Compressive strength, 25°C, psi	6000 - 10,000
Tensile strength, 25°C, psi	1400 - 2,000
Impact strength, ft·lb (1/4" thick specimen on concrete)	9 - 12
Abrasion resistance	0.004 - 0.008
Adhesion	Good

### Epoxy flooring Chemical Resistance, 70°F

Reagent	Value
Acetic acid, 5%	P
Aliphatic solvents (mineral spirits)	E
Ammonium hydroxide, 10%	G
Ammonium hydroxide, 30%	F
Boric acid	E
Citric acid, 10%	E
Esters	E
Ethers (Ethyl ether)	
Chlorinated solvents (Carbon tetrachloride)	F
Formaldehyde, 37%	G
Glycerine	G
Hydrocarbon	E
Hydrochloric acid, 10%	P
Hydrochloric acid, 37%	P
Acetone	F
Nitric acid, 10%	P
Sulfuric acid, 10%	P
Sodium hydroxide, 10%	G
Sodium hydroxide, 50%	F
Water (distilled)	E
Calcium chloride, 50% solution	E

E = Excellent - Suitable for long and perhaps permanent immersion

G = Good - Suitable for short immersion or prolonged spillage; F = Fair - Suitable for temporary spillage

P = Poor - Not recommended

### FDA Status

Cured coatings made with Aradur 125-2 BD hardener and other approved components meet the requirements of the Food & Drug Administration regulation 21 CFR 175.300, for the safe use as a food-contact surface under the conditions described in this section. Solvents are not covered and must be removed in the final coating.

### Storage

**Aradur® 140-2 Hardener** should be stored in a dry place, in the sealed original container, at temperatures between 2°C and 40°C (36°F and 104°F). Under these storage conditions, the product has a shelf life of **3 years** (from date of manufacture). The product should not be exposed to direct sunlight.

### Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

#### First Aid!

Refer to SDS as mentioned above.

**KEEP OUT OF REACH OF CHILDREN**

**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

## Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

**Araldite®** and **Aradur®** are a registered trademarks of Huntsman LLC or an affiliate thereof in one or more, but not all countries.

© 2016 Huntsman Advanced Materials Inc.

### Main Offices:

**Huntsman Corporation**  
10003 Woodloch Forest Dr  
The Woodlands, TX 77380  
888-564-9318

**Huntsman Advanced Technology Center**  
8600 Gosling Rd.  
The Woodlands, TX 77381  
281-719-7400